

KÖSTER

KB-FLEX 200 SEALING PASTE

Tehni ki podaci / Artikal broj

8.05

Važi od 28. Novembra 2011.

Trajno plasti na smola za zaptivanje

Opis



KB-Flex 200 je trajno plasti na smola za zatvaranje prodora, za kablove, cevi i sl., gde je prisutna vlaga i voda pod pritiskom. Ona se ne stvrdnjava ve ostaje u stanju meke smole i može se preoblikovati u svako doba.

Tehni ki podaci

Baza	poliolefin
Boja	siva
Spec.težina	1,60gr/cm ³
Temperatura otpor	+ 50°C
Konzistencija	Ne sливaju a pasta
Radna temperature	+5°C ±35°C
Temp. površine	+5°C ±30°C

Oblast primene

Zatvaranje prodora cevi i kablova u podrumima i nose im zidovima. Takode se može koristiti i za prodore vode.

Podloga

Suva, vlažna ili mokra. Površina mora biti bez masti, ulja, katrana i ostalih materija koje mogu da stvore kontra efekat za vezu sa površinom. Referentne podloge su beton, opeka, malter i sve druge konstrukcije od mineralnih materijala. KB-Flex 200 takođe vezuje za keramiku, PVC, polietilen i polipropilen.

Aplikacija

Zagrejati KB-Flex 200 do 30 °C u vodi pre po etka rada da dostigne odgovaraju u radnu konzistenciju. Pre primene KB Flex 200, barijera napravljena od brzovezu e PU pene, mora biti postavljena u dubinu do 10 cm. Staviti kertridž u pištolj i zatim pritisnuti kroz otvor kako bi rezultuju i sloj bio debljine minimum 8cm. KB-Flex 200 mora biti dimenzioniran na takav na in da odnos izmedju širine otvora i materijala nije manji od 1,5 do

1.Maksimalna širina otvora može biti 300mm.Nakon finiširanja popunjavanja protresite kabal i popunite materijalom mesta gde su nastale male šupljine usled pomicanja kabla.Osigurajte da cev ne trpi nikakva naprezanja.Kona no,kao zadnji korak,koristite smesu za zaptivanje u debljini od 1cm,postavite je, dobro utisnite i poravnajte sa metalnom špatulom.Kao dodatno osiguranje usta otvora se zatvaraju sa KOSTER KB Fix 5..Ako se postavlja novi kabal ukloniti KOSTER KB Fix 5, posle toga se kabal gura kroz postoje i KB-Flex 200.

Potrošnja

Oko 1.6kg/lit zapremine.

Pakovanje

850g ketridži,jedna kutija sadrži 20 ketridja.

Skladištenje

Na sobnoj temperaturi(20°C) do 2 god.

iš enje alata

Posle upotrebe o istiti KOSTER Bitumen Remover.

Koriš eni citati tehni kih listova;

KÖSTER Bitumen Remover

Art. Nr. 9.03

KÖSTER KB-FIX

Art. Nr. 5.01

The accurate and thereby effective and successful application of our products is not subject to our control. The guarantee can therefore only be applied to the quality of our products within the scope of our terms and conditions, not, however, for their effective and successful application. These guidelines replace all previous ones.